

CYRENE SILVER KNIGHT

Technical datasheet

COMMERCIAL

| Technical parameter | Standard | Unit | Result |
|--------------------------|---|-----------|---|
| DESCRIPTION | | | |
| Construction | Non-direction homogeneous floor covering with self-disinfecting surface | | |
| Binder content | EN ISO 10581 | class | Type I. |
| Total thickness | EN ISO 24346 | mm | 2,0 |
| Width of roll | EN ISO 24341 | m | 2 |
| Length of roll | EN ISO 24341 | lm | 20 |
| Total weight | EN ISO 23997 | kg/m2 | 2,8 |
| CLASSIFICATION | | | |
| European classification | EN 685 | class | 34/43 |
| PERFORMANCE | | | |
| Abrasion group | MSZ EN 660-1 | class | T |
| Residual indentation | EN ISO 24343 | max. mm | 0,1 |
| Dimensional stability | EN ISO 23999 | max.% | 0,2 |
| | EN ISO 23999 | average % | 0,1 |
| Fire resistance | EN 13501-1 | class | Bfl-s1 |
| Slip resistance | DIN 51130 | | R10 |
| | EN 13893 | | DS |
| Electrical resistance | EN 1815 | kV | < 2 |
| Chemical resistance | EN ISO 26987 | | ✓ |
| Bacterial resistance | EN ISO 846:1999 | | ✓ |
| Light fastness | EN 20105 B02 | grade | 6 |
| Castor chair resistance | EN ISO 4918 | | ✓ |
| Thermal resistance | EN 12524 | m2K/W | 0,012 |
| Surface treatment | | | SILVER KNIGHT iGUARD |
| Bacteriostatic activity | ISO 22196 | | ≥ 95% |
| Antiviral activity | ISO 21702 | | ≥ 99% |
| Environmental attributes | | | Phthalate, Solvent and Heavy metal free product |
| Seaming method | | | heat or cold weld |
| Warranty | | year | 15 |
| CE MARKING | EN 14041 | | ✓ |